



General Purpose Poly Styrene (GPPS) - GPPS 47

| Property | Unit | Test | Value |
|--------------------------|---------|-------------------------------------|-------|
| M | g/10min | D1238 | 3.8 |
| STYRENE RESIDUAL MONOMER | PPM | CLG LABPSG004 (ATOFINA TEST METHOD) | <500 |
| V | | D1525 | 99 |
| TENSILE STRENGTH | MPA | D638 | 50 |
| CHARPY IMPACT STRENGTH | Kj/m2 | D256 | 10 |
| FLEXURAL MODULUS | MPa | D790 | 3100 |