



Expandable Poly Styrene (EPS) - FC522

| Property | Unit | Test | Value |
|------------------|-------|---------------------------------|-------------------|
| BEAD SIZE | MM | SUNPOR 7.2.5 (MIN 90% BY WT) | (0.3-0.5)(>90%wt) |
| K-VALUE | | SUNPOR 7.2.4 | 55 |
| PENTANE CONTENT | WT% | SUNPOR 7.2.2 | >5.2% |
| BULK DENSITY | KG/M3 | SUNPOR 7.2.3 | 22-30 |
| RESIDUAL MONOMER | PPM | SUNPOR 7.2.1 | 500 |