



## Bitumen - 40/50

Property	Unit	Test	Value
S		ASTM D-70	1.01-1.06
P		ASTM D-5	40/50
S		ASTM D-36	52-60
D		ASTM D-113	100
Loss on Heating (%wt)		ASTM D-6	0.2 max
Drop in Penetration After Heating%		ASTM D-6 & D-5	20 max
F		ASTM D-92	250 min
Solubility In CS2 (%wt)		ASTM D-4	99.5 min
Organic Matter Insoluble In CS2(%wt)		ASTM D-4	
S		* A.A.S.H.O.T.102	negative