



Epoxy Resins(ER) - E-01X75

| Property | Unit | Test | Value |
|-----------------------|--------------|-----------------|---------------------------|
| Appearance | visual | visual | clear light yellow liquid |
| Epoxy equivalent | g/eq | ASTM D1652 | 434-555 |
| Epoxy value | mol/100g | ASTM D1652 | 0.180-0.230 |
| Color | Pt-Co (APHA) | ASTM 1209(APHA) | Max 100 |
| Viscosity | Mpas | D | 6000-12000 |
| Hydrolysable Chlorine | %wt | ASTM 1726 | Max 0.1 |
| %Non-Volatile | %wt | DIN EN ISO 3251 | 74-76 |