



## Acrylonitrile Butadiene Styrene (ABS) - ABS70SR

Property	Unit	Test	Value
Izod impact (6.4 mm , notched)	Kj/m2	D-256	Min25
M	gr/10 min	D-1238	Jul-14
Rock well hardness	R-scale	D-785	100-120
HDT ( 1.82 m pa)	?C	D-648	Min82
V	?C	D-1525	Min 94
T	Kg/cm2	D-638	Min 440
T	%	D-638	Min 16
F	Kg/cm2	D-790	Min 630
F	Kg/cm2	D-790	Min 18000
Specific Gravity ( 23?C)	.....	D-792	1.04
Molding Shrinkage	%	D-955	0.4-0.7
Flammability ( 1/8inch(3.2mm) )		UI94	HB