



## Poly Carbonate(PC) - PC710

Property	Unit	Test	Value
MFI (300 C)	g/10 min	ASTM D1238	7
Density	g	ASTM D792	1.2
Tensile Strength	Mpa	ASTM D638	? 60
Modulus of Elasticity	Mpa	ASTM D638	2
Elongation	%	ASTM D638	> 90
Dielectric Strength	Kv/mm	ASTM D149	? 20
Charpy Impact Strength	K	ASTM D6110	? 25
Vicat Soft. Temp.	C	ASTM D1525	1
Transmittance	%	ASTM D1003	? 80
Solvent Content	ppm	GC (int-st)	Max. 3000