



Bitumen - 80/100

Property	Unit	Test	Value
S		ASTM D-70	1.01-1.05
P		ASTM D-5	80-100
S		ASTM D-36	43 min
D		ASTM D-113	100 min
Loss on Heating (%wt)		ASTM D-6	0.5 max
Drop in Penetration After Heating%		ASTM D-6 & D-5	20 max
F		ASTM D-92	225 min
Solubility In CS2 (%wt)		ASTM D-4	99 min
Penetration Index			-1.142857143
S		* A.A.S.H.O.T.102	negative