



Linear Low Density Polyethylene (LLDPE) - Film - LL0220KJ

| Property | Unit | Test | Value |
|---------------------------------|--------------------|----------------|-----------|
| M | gr/10min | ASTM D 1238 | 2.3 |
| Density | gr/cm ³ | ASTM D 1505 | 0.92 |
| Haze | % | ASTM D 1003 | 12 |
| G | % | ASTM D 2457 | 30 |
| Anti Oxidant | | | ? |
| Anti Block | | | ? |
| Slip Agent | | | ? |
| Dart Drop Impact | g | ASTM D 1709(A) | 90 |
| Tear Strength MD/TD | gr/25?m | ASTM D 1922 | 100/300 |
| Tensile Strength at yield MD/TD | MPa | ASTM D 882 | 10:11 |
| Tensile Strength at Break MD/TD | Mpa | ASTM D 882 | 30/25 |
| Elongation at break MD/TD | % | ASTM D 882 | 1000/1100 |
| Secant Modulus MD/TD | Mpa | ASTM D 882 | 80/100 |
| Coefficient of friction | | ASTM D 1894 | 0.13 |
| Vicat Softening Temperature | | ASTM D 1525 | 100 |
| Melting Point | | BPC | 123 |